

What is Claimed is

Sub
A2
5 B1
1. A vital matter and a producing method thereof,
wherein the vital matter is prepared by the following
steps: 1) preparing a composition containing kaoline (white
soil) 30.0-40.0wt%, potassium sulfate 15.0-20.0wt%, sodium
sulfate 13.0-17.0wt%, feldspar 12.0-16.0wt%, talc 12.0-
16.0% and ferric oxide 0.5-1.5wt% (step 1); and 2) mixing
the above-mentioned compositin using a compressed molding
method (step 2); and 3) heating the mixed composition at
1000-1300°C (step3).

2. The vital matter and the producing method thereof
according to claim 1, wherein potassium sulfate and sodium
sulfate are replased by the same ratio of each molecular
weight of sodium chloride and sodium chloride.

Sub
A3
20 B2
3. The vital matter and the producing method thereof
according to claim 1, wherein the vital matter is composed
of potassium 19.06-23.29wt%, calcium 14.21-17.36wt%, sodium
12.30-14.97wt%, magnesium 11.98-14.64wt%, silicon 13.74-
16.80wt%, aluminium 12.21-15.13wt%, iron 3.48-4.26wt%,
titanium 0.95-1.17wt%, manganese 0.28-0.40wt%, zinc 0.17-
0.20wt%, germanium 0.07-0.09wt%, selenium 0.03-0.04wt% and
other elements 1.36-1.67wt%.

4. The vital matter and the producing method thereof

according to claim 1 wherein a composition of the
vital matter is used in combination with synthetic
resins after prepared in form of minute powder of 200-
350 mesh.

5

Add
A4

Add
B4

204770" 49647650